

TECHNICAL DATA SHEET NO: LJ550

VERSION: 1/11/2/08 PAGE: 1 of 3 PRINT DATE: 24/01/2015

LUMBERJACK 550



Colour	Product Code	Pack Size	Box Qty
Buff	LJACK5503	290ML	12
	LJACK5506	600ML	12

Product Description

Lumberjack 550 is a high specification, cartridge/foil applied product, specifically designed for fixing all types of wooden floors directly onto all common substrates, eliminating the need for battens. Lumberjack 550 is based on the latest developments in hybrid polymer technology.

Benefits

- *100% active, solvent and water free will not cause warpage or curl of wood blocks/planks.
- Permanently flexible compensates for subfloor movement. .
- Will bond wood directly to all common subfloors, e.g. concrete, wood, metal, ceramic tiled, vinyl, marble, granite and most natural stone floors.
- Suitable for use with underfloor heating (due to high flexibility)
- Odourless.
- Excellent gap filling properties for uneven surfaces
- Full bed elastic product gives excellent sound deadening/acoustic properties.

Limitations

- Always check with flooring manufacturer re: any specific instructions/requirements specifically relating to their flooring before fitting floors.
- Do not use against bitumen or substrates that bleed oil or plasticizers
- Do not use, store or allow to cure below +5°C.

Surface Preparation

The surfaces to be glued must be sound, clean, dry and free from dust, grease and other contaminants. Existing floors must be free from all polish/wax. Prime/stabilise friable concrete/anhydrite and floors with residual adhesive with Lumberjack M.B Primer before application. New concrete must be allowed 4 weeks to dry and mature. Always check moisture level of subfloor if moisture levels in subfloor are above those recommended by the flooring manufacturer, damp proof the floor with at least two coats of Lumberjack M.B Primer as directed. (See limitations section). Chipboard must be free of release agents/wax. Very porous or friable surfaces should first be primed with Lumberjack M.B Primer and allowed to dry. Basement/below ground floors must be adequately protected with a D.P.C and two coats of Lumberjack M.B Primer applied as directed. Under floor heating must be turned off 48 hours before and 48 hours after the adhesive has been applied.

FLOORING: The parquet flooring MUST be acclimatized for several days in the room where it is to be installed. Leave in original packaging during this period.



VERSION: 1/11/2/08

TECHNICAL DATA SHEET NO: LJ550

PAGE: 2 of 3 PRINT DATE: 24/01/2015

Application

All installations and sub floor preparations must be carried out in line with the relevant British or international standards. Cut of tip of sausage and place into suitable cartridge. Cut of top of nozzle flat to leave an 8mm opening. Cut a V shaped profile down into nozzle to a depth of approximately approx 10mm. Fix nozzle and place cartridge containing sausage in sealant gun. Hold gun at 90` to floor and extrude out a triangular shaped bead, approx 8mm wide and 10mm high at ca. 250mm centres at right angles to the length of the plank.

Position blocks/planks whilst adhesive is still tacky (within 30mins) and tap into final position with mallet and block, removing uncured adhesive with EVERBUILD WONDER WIPES. (Caution - test compatibility with lacquer finished block first)

Floor may be sanded/ trafficked 12-24 hours after application, depending on site conditions (longer at low temperatures).

If surface has no or little absorbency; allow 3 days before sanding/trafficking.

One 310ml Cartridge will bond approximately 1m2 of flooring when applied as directed. One 600ml sausage will bond approximately 2m2 of flooring when applied as directed.

Specific Data

Specific Data		
Base	STPE hybrid Polymer	
Specific Gravity	1.53g/cm3	
Solvent Content	Nil	
Colour	Buff	
Workability	Good, and grooves remain after application	
Viscocity: (HBDVII+/S70/10rpm)	250,000 – 300,000cps	
Tack Free	30 mins at 23°C and 50% RH	
Chemical resistance	Excellent	
Humidity and water resistance	Excellent	
Typical Shear strength	>1.2N/mm2 (24 hrs)	
(wood/wood)		
Alkali resistance	Excellent	
Application temps	+5-+30`C	
Temperature resistance	-40 to +80`C	
Trafficability/Sandability on	24 hours after fixing	
new floors		
Complete cure	36-48 hours.	
Minimum Screed requirements	28 days maturing and max 3% moisture content before using this	
	adhesive. For moisture contents at 3.1-7%, use in conjunction with	
	Lumberjack MB primer and moisture barrier. Do not use this	
	product above these recommended moisture levels.	

Health & Safety

Contains 3-(2-aminoethylamino)propyl trimethoxysilane and bis(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate. May produce an allergic reaction.

Consult MSDS for full list of hazards.

Storage

Store in cool, dry conditions between +5 and $+25^{\circ}$ C. Ensure good ventilation. Storage outside these parameters will dramatically reduce shelf life. Opened tins must be closed airtight and used up as soon as possible (within 1 month).



PRINT DATE: 24/01/2015

VERSION: 1/11/2/08

TECHNICAL DATA SHEET NO: LJ550

PAGE: 3 of 3

Shelf Life

12 months from date of manufacture when stored as directed.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.